

Ropanyl EM 4/1 00+02 black M1 AS HC NL /60ShD

Article code: SBRY579379

General information

Product group	Synthetic Belts
Industry segment	Textile
Main product feature	High conductivity
Indication of use	Slider bed, Rollers, Flat

Belt construction

Tension layer		polyester, stable
Number of plies		1
Top side	material	Ropanyl, TPU
	finish	smooth, M1 Fine matt finish
	color	black
Bottom side	material	Ropanol, PUR
	finish	impregnated fabric
	color	black

Characteristics

Food Grade (FG)	no	
Antistatic (AS)	yes	ISO 21178
High conductive (HC)	yes	ISO 284
Flame-retardant (FR)	no	
ATEX approval	no	

Technical data

Hardness	ISO 868	top side	60D Shore	
Force at 1% elongation (static)	ISO 21181		4 N/mm	22.84 lbs/in.
Thickness	AB method KV.002	total	0.75 mm	0.03 in.
		top cover	0.25 mm	0.01 in.
Weight	AB method KV.004		0.8 kg/m ²	0.16 lbs/ft ²
Operating temperature	continuous	from / to	-20 / 70 °C	-4 / 158 °F
Minimum pulley diameter	flexing		25 mm	0.98 in.
	backflexing		50 mm	1.97 in.
Manufacturing width	standard		3400 mm	133.86 in.
	maximum		3000 mm	118.11 in.

Fabrication

Hot splicing is always preferable. Glueing can only be done when the belt is exposed to normal temperature and the humidity is not excessive. For the working method, consult the splice information and the equipment literature. Apply the recommended splice as indicated in the separate information.

Additional information

This sheet contains typical values, which apply to a temperature of approx. 20 °C (68 °F), unless otherwise stated, individual data may differ. We recommend to keep the belt tension to a practical working minimum to maximize the service life of the belt and machine parts. Always protect belts from sunlight/UV-radiation, avoid temperatures below 10°C and above 40°C, dust and dirt. Store belts in a cool and dry place and if possible in their original packaging. For details consult 'Storage and handling instructions' or contact our specialist.